

# Stretch Film

Orbit Air B (High Performance Pre-Stretched Hand Wrap)

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

Test	Values (listed by film thickness)	
	Reference Methods	30 gauge 7.6 micron 0.30 mil
<b>Ultimate Tensile MD</b> (psi)	ASTM D882	13,000
<b>Ultimate Tensile TD</b> (psi)	ASTM D882	3200
<b>Elongation MD</b> (%)	ASTM D882	162
<b>Elongation TD</b> (%)	ASTM D882	650
<b>Tear Resistance MD</b> (grams and g/mil)	ASTM D1922	66 grams
		219 g/mil
<b>Tear Resistance TD</b> (grams and g/mil)	ASTM D1922	232 grams
		773 g/mil

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warranties or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA  
 Customer Service: 800.IPG.8273 | 800.474.8273  
 Tape Technical Service: 877.447.4832  
[www.itape.com](http://www.itape.com) | [info@itape.com](mailto:info@itape.com)

EFFECTIVE: 04/14

