

# sytec® SP6

**SYTEC SP6** is a transparent antistatic shrink film with superior static control capabilities. Provides an environmentally friendly packaging concept for in-process bundling and ESD overwrap for electronic components, computer parts, and more.

### SPECIAL FEATURES

- Longterm antistatic protection
  - Amine-free
- Stable surface resistivity for up to 2 years

### SHRINK & SEAL PROPERTIES

- Easy to seal on standard machinery
- Quick shrinkage in heated tunnel

*Recyclable & Amine Free*

PROPERTY	METHOD	VALUES	STANDARD LIMITS
<b>Surface Resistivity</b>  Before shrinkage After shrinkage	ASTM D-257 Mil-B-81705C EIA 541	$1 \times 10^{11} \Omega/\square$ $2 \times 10^{11} \Omega/\square$	$< 10^{12} \Omega/\square$
<b>Static Decay Rate</b>  Before shrinkage After shrinkage	FTMS 101C Method 4046.1	0.2 seconds 0.4 seconds	$< 2 \text{ sec}$
<b>Triboelectric charge Generation</b>	EIA 541	$< 0.2 \text{ NCB}/\square$	
<b>Density</b>	ASTM D-1505	$0.92 \text{ gr}/\text{cm}^3$	
<b>Shrinkage</b>	ANSI/ASTM D-2732	MD 50% TD 60%	

nominal thickness / gauge		100
yield	in <sup>2</sup> /lb	31200
reel length	ft (flat)	5250
	ft (c/f)	2625
nominal thickness / microns		25
yield	m <sup>2</sup> /kg	44
reel length	SW/m	1600
	CF/m	800

## FOOD CONTACT

SYFAN SHRINK FILMS comply with the requirements and regulations which state that materials may be safely used in food contact applications, as described in the code of Federal Regulations of the U.S. Food and Drug Administration Title 21 para. 177.1520 and in the Commission Directive No. 2011/10/EU – U – L 34, 9.2.11, EU 1935/2004, and EC 90/128/EEC Official Journal of European Communities, No. L75/19.



SYFAN -SAAD  
has been  
ISO-certified since  
June 1994.



## SAFETY & ENVIRONMENT

SYFAN SYTEC SHRINK FILMS contain no CFC's nor any residues of the heavy metals Sb, Cr, As, Pb, Ba, Cd, Ag, Se. The gas generated during sealing of SYTEC shrink film is comprised of hydrocarbon derivatives of the pure raw material and contains no harmful substances, irritants, or chlorine derivatives.

SYTEC SP6 film should be stored in a cool, dry environment away from direct sunlight. Maximum storage temperature: 25°C / 77°F. The above table is based on test data believed to be reliable. Since it is not possible to anticipate the different and varying conditions under which SYFAN films may be used, purchasers are advised to carry out their own tests to determine the suitability of SYFAN products for their specific purposes.

**SYFAN® and SYTEC® are registered trade marks of SYFAN SAAD Israel.**



**DARTRONICS, INC.**

PACKAGING AUTOMATION SPECIALISTS



150 WILLIAM ST. PERTH AMBOY, NJ 08861 / TOLL FREE: 800-298-8936 / PHONE: 732-324-0800 / FAX: 732-324-4488

WWW.DARTRONICS.COM

YOUTUBE / DARTRONICS

THE SINGLE SOURCE FOR YOUR

**END-OF-LINE**

PACKAGING, MARKING AND CODING NEEDS